

LABORATORY WORKTOPS INTERIOR PANELS



Think Trespa



TRES|PA®



TRESPA TOPLAB^{ECO-FIBRE} – A CHOICE FOR THE FUTURE

Selecting the right material for laboratory worktops and furniture is never easy. Hygiene, cleanliness, chemical and stain resistance are essential, and worktops in particular need to be hygienic, easy to clean and maintain, durable and flexible.

Increasingly, there is also an additional need to find environmentally friendly solutions – to minimize ecological impact and maximize sustainability.

It is with this firmly in mind that Trespa has introduced Trespa TopLab^{ECO-FIBRE}, a panel that combines natural aesthetics with outstanding chemical performance, while at the same time making a significant contribution to the preservation of limited natural resources.

Color-through core for great natural appearance

Trespa TopLab^{ECO-FIBRE} is available in two contemporary and attractive colors. These panels have a color-through core to allow the creation of a natural and attractive laboratory environment.

The color options are Sahara – a sandy beige tone, and Amazon – a dark green with gray undertones. These two colors are produced from natural wood fibers, combined with resin and pigments. The inherent characteristics of the wood fibers create a natural variation in color and appearance both within the same panel and from sheet to sheet, enhancing the overall natural design.

Strong commitment to the environment


Trespa TopLab^{ECO-FIBRE} is a durable, easy-to-clean and low maintenance material made from sustainable resources. The panels consist of thermosetting resins, homogeneously reinforced with certified wood fibers, harvested from European forests and manufactured under high pressure and at high temperatures.

Its wood fiber base makes Trespa TopLab^{ECO-FIBRE} an environmentally sound solution, which is certified by the Programme for the Endorsement of Forest Certification schemes (PEFC), the world's largest forest certification organization.

With a growing demand for more environmentally sustainable products, Trespa TopLab^{ECO-FIBRE} is the choice material for planners and customers who want to make a positive impact on the environment. Trespa TopLab^{ECO-FIBRE} can contribute to US Green Building Council LEED® credits.

Proven chemical resistance

Trespa TopLab^{ECO-FIBRE} is a unique material that combines outstanding chemical resistance with a color-through core. Thanks to Trespa's Electron Beam Curing (EBC) technology and its transparent topcoat, the surface is completely pore-free and resistant to a large number of aggressive chemicals; wear and water resistant; easy to clean, disinfect and maintain.



TRESPA TOPLAB^{ECO-FIBRE} – SUSTAINABLE FROM EVERY PERSPECTIVE

High aesthetics, low maintenance

Trespa TopLab^{ECO-FIBRE} sets new standards in laboratory aesthetics. Panels have a smooth surface. This makes them highly suitable for multi-functional surfaces on which activities can be combined: from placing laboratory equipment and computers to carrying out specific analysis and research to more general work, such as administration. Worktops and furniture are easy to keep clean and will keep their appearance for many years to come, even when in constant use.

Color all the way through


Trespa is the first manufacturer to produce color-through laboratory worktop based on Trespa's Dry Forming (DF) technology. The natural look and the warm and natural colors of Trespa TopLab^{ECO-FIBRE} enable designers to create highly individual laboratory environments. In the unlikely event that a surface is damaged, the color-through panel will retain its color.

Because the panels are created with natural wood fibers, Trespa TopLab^{ECO-FIBRE} is subject to slight variations in color both within one panel and from sheet to sheet. This enhances the natural look of the material and highlights the individuality of the laboratory design.

Trespa supports long-term sustainability

Trespa was one of the first manufacturers of construction products to map the totality of its products effects by means of a life-cycle analysis (LCA), right from the source of the raw materials to the end of the life-cycle.

Trespa International was one of the first producers of panel material to be certified in 1999 according to ISO 14001, awarded by Lloyd's Register. The ISO 14001 standard describes the steps required for setting up, implementing, maintaining and improving a completely integrated environmental management system.





Trespa TopLab^{ECO-FIBRE} and PEFC Certification

With a need to find environmentally sound solutions, public authorities and corporate procurement policies increasingly demand reassurance and/or proof that the wood they use in their applications comes from sustainably managed forests. The Programme for the Endorsement of Forest Certification schemes (PEFC), the world's largest forest certification organization, offers a reliable and credible mechanism to prove to their customers where the wood for their products has come from.

The certification of Trespa TopLab^{ECO-FIBRE} provides transparent and independent proof that the wood materials used in its manufacture fully comply with PEFC requirements. Moreover, Trespa International has achieved the new step of integrating the PEFC Chain of Custody system in its environmental management system.

Chain of Custody certification is the tracking of wood (based) products from the forest of origin to the final product. By providing a written assessment from an independent, qualified and accredited expert that the wood flow accounting system meets the exacting requirements of the certification scheme, customers can be absolutely sure that their product is linked to certified forests.

Global recognition

In addition, Trespa TopLab^{ECO-FIBRE} is recognized by national and international certification authorities around the world. Trespa TopLab^{ECO-FIBRE} is GREENGUARD Indoor Air Quality Certified® and has achieved GREENGUARD for Children & SchoolsSM Certification.

Trespa TopLab^{ECO-FIBRE} can contribute to US Green Building Council LEED® credits.



PEFC certified

Trespa TopLab^{ECO-FIBRE} is from sustainably managed forest and controlled sources.

www.pefc.org



TRESPA TOPLAB^{ECO-FIBRE} - HIGH AESTHETICS, LOW MAINTENANCE

Cleanability and hygiene

Trespa TopLab^{ECO-FIBRE} is designed to deliver an outstanding performance in a laboratory environment, where hygiene is key. Its surface is close to impervious to all possible materials used in biochemical and medical laboratories: radio-isotopes, human tissue and blood samples or bacteria. Biological or clinical test results are dependent on non-contamination. The Trespa TopLab^{ECO-FIBRE} surface is impermeable to most bacteria, molds or micro-organisms. Resistant to dyes and organic solvents, Trespa TopLab^{ECO-FIBRE} is water-resistant and remains easy to clean or disinfect.

Chemical resistance

Trespa TopLab^{ECO-FIBRE} is resistant to a large number of aggressive chemicals. They will not mark the surface if cleaned within 24 hours. Test results show the panel's 24 hour resistance (see separate test datasheet).

Durability

Trespa TopLab^{ECO-FIBRE} is ideal for use in a multi-functional environment. Used in worktops and other applications, the material is versatile and provides a tough and long-lasting surface that will retain its good looks for many years. Used as part of a mobile and flexible environment, Trespa TopLab^{ECO-FIBRE} delivers added strength to any laboratory or lecture room.



DISCLAIMER

General

These terms apply to the use of this document and such use automatically means that the other party agrees to these terms. The information provided by Trespa International B.V. ("Trespa") in this document is solely indicative. Trespa is unable to warrant the accuracy and completeness of this information. Trespa may change the information included in this document at any time and without further notice. Trespa's customers and third parties must ascertain that they have the most recent document (for the most recent version, please consult: www.trespa.com). No rights can be derived from the information provided; the use of the information is at the other party's risk and responsibility.

Trespa does not warrant that the information in this document is suitable for the purpose for which it is consulted by the other party. This document does not contain any design, structural calculation, estimate or other warranty or representation that customers and third parties may rely on. This document does not guarantee any properties of Trespa products. Colors used in Trespa's communications (including but not limited to printed matter) and in samples of Trespa's products may differ from the colors of the Trespa products to be supplied. Samples are not intended for use in product tests

and are not representative of characteristics of the Trespa products. Trespa's products and samples are produced within the specified color tolerances and the colors (of production batches) may differ, even if the same color is used. The viewing angle also influences the color perception. Metallics panels feature a surface whose color appears to change based on the direction from which it is viewed. The specified color stability and color specifications relate only to the decorative surface of the Trespa products, not to the core material and samples of the Trespa products. Trespa products are delivered ex-works with straight, sawn sides.

Customers and third parties must have a professional adviser inform them about (the suitability of) the Trespa products for all desired applications and about applicable laws and regulations. Trespa does not warrant the above.

The most recent version of the current delivery program and the Material Properties Datasheet can be found at www.trespa.info. Only the information in the most recent and valid Material Properties Datasheet should be used to select and provide advice regarding Trespa products. Trespa reserves the right to change (the specifications for) its products without prior notice.

Liability

Trespa is not liable (neither contractual nor non-contractual) for any damage arising from or related to the use of this document, except if and to the extent that such damage is the result of willful misconduct or gross negligence on the part of Trespa and/or its management. The limitation of liability applies to all parties affiliated with Trespa, including but not limited to its officers, directors, employees, affiliated enterprises, suppliers, distributors, agents, and representatives.

General conditions

All oral and written statements, offers, quotations, sales, supplies, deliveries and/or agreements and all related activities of Trespa are governed by the Trespa General Terms and Conditions of Sale (*Algemene verkooppvoorwaarden Trespa International B.V.*) filed with the Chamber of Commerce and Industry for Noord- en Midden-Limburg in Venlo (NL) on 11 April 2007 under number 24270677, which can be found on and downloaded from the Trespa website, www.trespa.com.

All oral and written statements, offers, quotations, sales, supplies, deliveries and/or agreements and all related work of Trespa North America, Ltd. are governed by the Trespa General Terms and Conditions of Sale, which can be found on and downloaded from the Trespa North

America Ltd. website, www.trespa.com/na. A copy of these general conditions of sale will be provided free of charge on request.

All general terms and conditions other than the conditions mentioned above are dismissed and do not apply, regardless of whether such terms and conditions are referred to on requests for offers, offer confirmations, stationery and/or other documents of the other party, even if Trespa does not expressly object to such terms and conditions.

Intellectual property

All intellectual property rights and other rights regarding the content of this document (including logos, text and photographs) are owned by Trespa and/or its licensors. Any use of the content of this document, including distribution, reproduction, disclosure, storage in an automated data file or the dispatch of such a file without Trespa's prior written consent is explicitly prohibited. © Trespa, Meteon, Athlon, TopLab, TopLab^{PLUS}, TopLab^{ECO-FIBRE}, Virtuton, Volkern, Trespa Essentials and Mystic Metallics are registered trademarks of Trespa.

Questions

Should you have any questions or comments, please do not hesitate to contact Trespa.

www.trespa.com

VISIT US

Trespa Design Centre New York

62 Greene Street (Ground Floor)
New York, NY 10012
United States of America
Tel.: 1-212-334-6888
Fax.: 1-866-298-3499
info.ny@trespa.com
www.trespa-ny.com

Trespa Design Centre Barcelona

Calle Ribera 5,
08003 Barcelona
Spain
Tel.: +34 (0) 93 295 4193
Fax.: +34 (0) 93 116 3300
info.barcelona@trespa.com
www.trespa-barcelona.com

CONTACT US

Trespa International B.V.

P.O. Box 110, 6000 AC Weert
Wetering 20, 6002 SM Weert
The Netherlands
www.trespa.com

Customer Service Desk EMEA Export

Tel.: +31 (0) 495 458 359 / 573
Fax: +31 (0) 495 458 383
infoexport@trespa.com

Trespa North America Ltd.

12267 Crosthwaite Circle
Poway, CA 92064
United States of America
Tel.: 1-800-487-3772
Fax: 1-858-679-9568
info.northamerica@trespa.com

Trespa China Co. Ltd.

Room 2604-05, HuaiHai Plaza
No. 1045 HuaiHai Road (central)
ShangHai 200031
P.R. China
Tel.: +86 (0) 21 6288 1299
Fax: +86 (0) 21 6288 1296
infochina@trespa.com

Customer Service Desk Asia/Pacific

Tel.: +86 (0) 21 5465 8388
Fax: +86 (0) 21 5465 6989
infoapac@trespa.com

Trespa UK Ltd.

Grosvenor House
Hollinswood Road
Central Park, Telford
Shropshire, TF2 9TW
United Kingdom
Tel.: +44 (0) 1952 290707
Fax: +44 (0) 1952 290101
info@trespa.co.uk



Your Trespa representative :

code V4661 version 3.0
date 08-18-2011 copies 0

Please visit www.trespa.com
for the most up to date version
of this document.

TRESPA TOPLAB^{ECO-FIBRE} – THE NATURAL CHOICE FOR LABORATORIES

Laboratories need to be functional and durable. Now they can also be aesthetically and environmentally sound. New Trespa TopLab^{ECO-FIBRE} is designed to maintain its design features in high traffic and challenging conditions.


Color-through core for great natural appearance

Trespa TopLab^{ECO-FIBRE} panels are available in two colors and have a color-through core. The color options are Sahara – a sandy beige tone, and Amazon – a dark green with gray undertones. These two colors are produced from natural wood fibers in combination with resin and pigments. The wood fibers' inherent characteristics create a natural variation in color and appearance both within the same panel and from sheet to sheet, enhancing the overall natural design.

PEFC Certification – Commitment to the environment

As a material made from sustainable resources, Trespa TopLab^{ECO-FIBRE} has been certified by the Programme for the Endorsement of Forest Certification schemes (PEFC). The PEFC Council is an independent, non-profit, non-governmental organization which promotes sustainably managed forests through independent third party certification and supported by 149 governments in the world covering 85% of the world's forest area.

Trespa TopLab^{ECO-FIBRE} can contribute to US Green Building Council LEED® credits.



PEFC certified

Trespa TopLab^{ECO-FIBRE} is from sustainably managed forest and controlled sources.

www.pefc.org

The colors in this document are printed, and therefore, cannot accurately represent the natural variation in Trespa TopLab^{ECO-FIBRE} color shades. Also gloss and surface texture may vary slightly from the original panel. Original samples are available on request.

TRESPA TOPLAB^{ECO-FIBRE} - CHEMICAL RESISTANCE

Test procedure

The test was conducted by applying 5 drops of each reagent on the surface, covered with a watch glass (except those marked**). Chemicals marked ** were tested with a saturated cotton ball covered by a bottle. All chemicals were tested at room temperature, rinsed off with water and evaluated.

Test results

No effect	0	No detectable stain, loss of gloss or change in work surface material
Excellent	0.5	Slight stain or loss of gloss, but no change to the function, smoothness or life of the work surface material
Good	1.0	A clearly discernible stain or loss of gloss, but no change to the function, smoothness or life of the work surface material.
Fair	2.0	Unacceptable staining or discernible deterioration or etching of the work surface material
Failure	3.0	Severe stain or moderate deterioration, pitting cratering or etching of work surface material

The chemicals mentioned in the table include chemicals/concentrations listed by SEFA 8 (Scientific Equipment and Furniture Association).

All information is based on our current state of knowledge. It is intended as information concerning our products and their application possibilities, and is therefore not intended as any form of guarantee with regard to any specific product characteristic. Test results differ per color.

Although the tests have been conducted according to the standard, it is recommended that users conduct their own tests on Trespa TopLab^{ECO-FIBRE}!

		TE-02 Amazon	TE-05 Sahara
Acids			
Acetic Acid	99 %	0	0
Acid Dichromate	5 %	0	0
Chromic Acid	60 %	0	0
Hydrochloric Acid	10 %	0	0
Hydrochloric Acid	37 %	0	0
Hydrofluoric Acid	48 %	3.0	3.0
Nitric Acid	20 %	0	0
Nitric Acid	30 %	0	0
Nitric Acid	65 %	1.0	1.0
Nitric Acid	70 %	1.0	1.0
Nitric Acid 65 %: Hydrochloric Acid 37 %	(1:3)	0	0
Perchloric Acid	60 %	0	0
Phosphoric Acid	85 %	0	0
Sulphuric Acid	25 %	0	0
Sulphuric Acid	33 %	0	0
Sulphuric Acid	98 %	0.5	0.5
Sulfuric Acid 77 %: Nitric Acid 70 %	(1:1)	0.5	1.0
Sulfuric Acid 85 %: Nitric Acid 70 %	(1:1)	0.5	1.0
Bases		TE-02 Amazon	TE-05 Sahara
Ammonium Hydroxide	28 %	0	0
Sodium Hydroxide	10 %	0	0
Sodium Hydroxide	20 %	0	0
Sodium Hydroxide	40 %	0	0
Sodium Hydroxide Flake		0	0
Salts		TE-02 Amazon	TE-05 Sahara
Copper Sulphate	10 %	0	0
Ferric (III) Chloride	10 %	0	0
Potassium Iodite	10 %	0	0
Potassium Permanganate	10 %	0	0
Saturated Zinc Chloride		0	0
Silver Nitrate	1 %	0	0
Sodium Chloride	10 %	0	0
Sodium Hypochlorite	13 %	0	0
Halogens		TE-02 Amazon	TE-05 Sahara
Iodine (Crystals)		0.5	0.5

Iodine Solution (0.1 N)		0.5	0.5
Tincture of Iodine		0	0
Organic Chemicals		TE-02 Amazon	TE-05 Sahara
Cresol		0	0
Dimethylformamide		0	0
Formaldehyde	37 %	0	0
Furfural		0	0
Gasoline		0	0.5
Hydrogen Peroxide	3 %	0	0
Phenol	90 %	0	0
Sodium Sulfide Saturated		0	0
Solvents**		TE-02 Amazon	TE-05 Sahara
Acetic Anhydride		0	0
Acetone		0	0
Acetonitrile		0	0
Amyl Acetate		0	0
Benzene		0	0
Butyl Alcohol		0	0
Carbon Tetrachloride		0	0
Chloroform		0	0
Dichlor Acetic Acid		0	0
Dichloromethane		0	0
Dioxane		0	0
Diethyl Ether		0	0
Ethylacetate		0	0
Ethylalcohol		0	0
Ethylene Glycol		0	0
Methylalcohol		0	0
Methylene Chloride		0	0
Methylethylketone		0	0
Methylisobutylketone		0	0
Mono Chlorobenzene		0	0
Napthelene		0	0
n-Butyl Acetate		0	0
Tetrahydrofurane		0	0
n-Hexane		0	0
Toluene		0	0
Trichloroethylene		0	0
Xylene		0	0
Biological Stains		TE-02 Amazon	TE-05 Sahara
Acridine Orange	1%	0	0
Alizarin Complexone Dihydrate	1%	0	0
Aniline Blue, Water Soluble	1%	0	0
Basic Fuchsin	1%	0	0
Carbol Fuchsin	1%	0	0
Carmine	1%	0	0
Congo Red	1%	0	0
Gentian Violet (dye)	1%	0	0
Eosin B	1%	0	0
Giemsa Stain	1%	0	0
Malachite Green Oxalate	1%	0	0
Methyl Violet 2B	1%	0	0
Methylene Blue	1%	0	0
Safranin O	1%	0	0
Sudan III	1%	0	0
Wright Stain	1%	0	0
Most conventional cleaning agents		TE-02 Amazon	TE-05 Sahara
		0	0

Please check www.trespa.info for the latest version of the material properties and delivery program.